




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : B05D 3/00, B32B 5/24 D02G 3/00, D03D 25/00	A1	(11) International Publication Number: WO 93/24241 (43) International Publication Date: 9 December 1993 (09.12.93)
(21) International Application Number: PCT/US93/05119 (22) International Filing Date: 28 May 1993 (28.05.93) (30) Priority data: 07/891,236 29 May 1992 (29.05.92) US (60) Parent Application or Grant (63) Related by Continuation US 07/891,236 (CIP) Filed on 29 May 1992 (29.05.92) (71) Applicant (for all designated States except US): TRIANGLE RESEARCH AND DEVELOPMENT CORPORA- TION [US/US]; 8921 Glenwood Avenue, Raleigh, NC 27612 (US).		(72) Inventors; and (75) Inventors/Applicants (for US only) : BRYANT, Yvonne, G. [US/US]; 316 Lord Berkeley Road, Raleigh, NC 27610 (US). COLVIN, David, P. [US/US]; Route 5, Box 67, Apex, NC 27502 (US). (74) Agents: BURTON, Carol, W. et al.; Holland & Hart, 555 17th Street, #2900, Denver, CO 80202 (US). (81) Designated States: BR, CA, JP, KR, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: FABRIC WITH REVERSIBLE ENHANCED THERMAL PROPERTIES

**(57) Abstract**

A coating (10) is adapted to be applied to a substrate (50) such as a fabric in order to enhance the thermal characteristics thereof. The coating includes a polymer binder (20) in which are dispersed integral and leak-resistant microcapsules (30) filled with phase change material (40) or plastic crystals that have specific thermal properties at predetermined temperatures.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

FABRIC WITH REVERSIBLE ENHANCED THERMAL PROPERTIES

FIELD OF THE INVENTION

This invention relates generally to the field of coated fabrics and more particularly to fabrics coated with a binder containing microcapsules filled with energy absorbing phase change material which enables the fabric to exhibit extended or enhanced heat retention or storage properties.

BACKGROUND OF THE INVENTION

The treatment of textiles with various substances in order to change the properties thereof is well known. For example, it is known that textiles may be waterproofed by coating them with natural or synthetic rubber. Substances have been developed which when sprayed onto fabrics introduce the property of stain resistance. Also known is the example of a fragrance delivery system which uses breakable fragrance-filled microcapsules which are attached to the surface of a fabric or fiber and upon the introduction of an external force, the microcapsules break releasing the fragrance over an extended time period.

Other examples of microcapsules being applied to the surface of fabrics for various end-uses are known. U.S. no. 4,774,133 to Doree et al. discloses a thermoplastic substrate bearing rupturable microcapsules in a binder. The substrate is capable of being softened when heated, and by the application of pressure the microcapsules become partially imbedded in the surface of porous objects such as fabrics. A thermo-adhesive textile product is disclosed in U.S. Patent No. 4,990,392 and comprises a backing fabric and an adhesive layer deposited on its surface. The adhesive layer comprises a thermo-adhesive polymer and a cross-linking agent which is isolated from the polymer by microencapsulation and which is freed by external action. The present invention differs from the forgoing examples in that the

microcapsules contain phase change material and are designed to be an integral and permanent part of a coating applied to a substrate, as opposed to being ruptured during use.

5 Fabrics have been given enhanced thermal properties by coating the fibers with phase change material and plastic crystals. U.S. Patent No. 4,871,615 discloses temperature adaptable textile fibers which store heat when the temperature rises and release heat when the
10 temperature decreases, in which phase change or plastic crystalline materials are enclosed within hollow fibers or impregnated upon non-hollow fibers. The fibers are produced by dissolving the phase change or plastic crystalline materials in a solvent such as
15 water, thereafter filling the hollow fibers, or impregnating the non-hollow fibers, with the solution, followed by removal of the solvent. Alternatively, the phase materials may be applied to the fibers from a melt rather than a solution.

20 At the phase change temperature, a characteristic of phase change material during the heating cycle is to absorb and hold a quantity of thermal energy at almost a constant temperature while changing to the next phase. Thus, the material can be precooled and used as a barrier
25 to heat, since a quantity of thermal energy must be absorbed by the phase change material before its temperature can rise. The phase change material may also be preheated and used as a barrier to cold, as a quantity of heat must be removed from the phase change material
30 before its temperature can begin to drop.

 However, the durability of the aforementioned surface mounted phase change materials was found to be lacking. While somewhat effective, the fabric lacked repeatability of the thermal response. Each successive
35 laundering removed a portion of the phase change material, thus causing the fabric to exhibit a

corresponding change in thermal properties which limited its usefulness and lifetime. As a result, further work was undertaken to perfect a series of process steps for binding the phase change material to the fabric in order to extend the useful life of the enhanced thermal properties. Furthermore, as far as is known to the inventors, these fibers and fabrics have limited usefulness as only a single phase change material may be applied to the substrate which requires that the thermal absorption or release occur at a specific temperature.

It is, therefore, an object of the present invention to provide a substrate coating with enhanced thermal retention properties.

It is another object of the present invention to provide a substrate coating which will maintain its enhanced thermal properties over an extended period of time.

It is another object of the invention to provide a substrate coating having enhanced thermal properties which can be produced with a minimum of process steps.

It is a still further object of the present invention to provide a substrate coating having enhanced thermal properties which can be applied to a fabric from which articles of clothing and the like can be manufactured.

It is a still further object of the present invention to provide a substrate coating which displays enhanced thermal properties over a specified temperature range.

A related object of the present invention is to provide a thermal control material having enhanced thermal storage properties that are reversible.

SUMMARY OF THE INVENTION

The foregoing objects are accomplished by providing a coating adapted to be applied to a substrate such as a fabric for enhancing the thermal storage properties

thereof. The coating comprises a polymer binder and a plurality of leak resistant microcapsules, integral with and dispersed throughout the polymer. The microcapsules contain a temperature stabilizing means such as a phase change material. A substrate coated with the object of the present invention exhibits enhanced thermal stability when subjected to heat or cold. The microcapsules are resistant to leakage or rupture and may be subjected to repeated external mechanical stresses with minimum changes in the thermal characteristics of the coated substrate. Additionally, the coating may also include microcapsules containing different preselected phase change materials with different transition temperatures, which increases the range of temperatures over which the coated substrate can be stabilized.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a cross section of a microcapsule according to the present invention containing phase change material.

Figure 2 is a perspective view of a substrate coated with a polymer coating microcapsule according to the present invention.

Figure 3 is a sectional view of a substrate coated on one side according to the present invention.

Figure 4 is another perspective view of a coated substrate according to the present invention.

Figure 5 is a cross-sectional view of the substrate according to the present invention taken along line 3-3 of Figure 4.

Detailed Description Of The Preferred Embodiments

While the present invention will be described more fully hereinafter, it is to be understood at the outset that persons of skill in the art may modify the invention herein described while still achieving the favorable results of this invention. Accordingly, the description which follows is to be understood as being a broad

teaching disclosure directed to persons of skill in the appropriate arts, and not as limiting upon the present invention.

Referring now to the drawings and particularly to Figures 2 and 4, the coating generally indicated at 10 comprises a flexible polymer binder 20, with a plurality of microcapsules 30 (Fig. 1) integral and dispersed throughout the polymer binder 20. The microcapsules 30 contain a temperature stabilizing means 40 as will be more fully explained hereinafter.

The polymer binder may take the form of an organic plastic, examples of which include, but are not limited to, polyurethane, nitrile rubbers, chloroprene rubbers, polyvinyl alcohol, silicone, ethylene/vinyl acetate copolymer, acrylic and the like.

The microcapsules 30 can range in size from about 0.5 to 1,000 microns and are formed according to conventional methods well known to those skilled in the art.

The microcapsules contain a temperature stabilizing means or phase change material 40 such as eicosane. Additionally, plastic crystals such as 2,2-dimethyl-1,3-propanediol (DMP) and 2-hydroxymethyl-2-methyl-1,3-propanediol (HMP) and the like may be used as the temperature stabilizing means. When plastic crystals absorb thermal energy, the molecular structure is temporarily modified without changing the phase of the material.

In another aspect of the invention, the composition of the phase change material 40 may be modified to obtain optimum thermal properties for a given temperature range. For example, the melting point of a homologous series of paraffinic hydrocarbons is directly related to the number of carbon atoms as shown in the following table:

	Compound Name	Number of Carbon Atoms	Melting Point ° Centigrade
	n-Octacosane	28	61.4
	n-Heptacosane	27	59.0
5	n-Hexacosane	26	56.4
	n-Pentacosane	25	53.7
	n-Tetracosane	24	50.9
	n-Tricosane	23	47.6
	n-Docosane	22	44.4
10	n-Heneicosane	21	40.5
	n-Eicosane	20	36.8
	n-Nonadecane	19	32.1
	n-Octadecane	18	28.2
	n-Heptadecane	17	22.0
15	n-Hexadecane	16	18.2
	n-Pentadecane	15	10.0
	n-Tetradecane	14	5.9
	n-Tridecane	13	-5.5

20 Each of the above materials can be separately encapsulated and is most effective near the melting point indicated. It will be seen from the foregoing that the effective temperature of the coating can be tailored to a specific environment by selecting the phase change materials required for the corresponding temperature and adding microcapsules containing the material to the coating.

25 In fabricating the coating 10, the desired microencapsulated phase change materials are added to the polymer binder (liquid, solution or dispersion), compounded, cured, cross-linked or foamed to form a flexible layer on a substrate such as a fabric according to conventional coating methods. Typical concentrations of microencapsulated phase change material 30 added to

the polymer binder range from about 30% to about 80% by weight. Embedding the microcapsules directly within the polymer binder 20 adds durability as the phase change material is protected by a dual wall, the first being the wall of the microcapsule and the second being the surrounding polymer matrix itself. Thus, the phase change material is less likely to leak from the coating during its liquid phase, thus enhancing its life and repeatability of thermal response.

The base material or substrate 50 can be an individual fiber, fabric (woven, knitted or non-woven) or non-fabric (molded objects). A significant element of the present invention is the continuous (webbed) or discontinuous (non-webbed) nature of the coating. Depending on fabric construction and viscosity of the coating medium, a discontinuously coated substrate 50 can be formed in which the individual elements of the substrate are each covered and not connected, as distinguished from a continuous coating in which the individual elements of the substrate 50 are connected by webbing of the coating matrix. Loose fabric construction coupled with a low viscosity coating medium yields the non-webbed structure, whereas tight fabric construction and high viscosity coating medium yields a coating with the webbed structure. In addition, individual fibers, Figures 4 and 5, can be coated before conversion into a product.

In one embodiment of the invention, the binder with microcapsules is sprayed onto a substrate. A polyurethane containing polytertamethyleneglycol ether reacted with methylene diphenylene diisocyanate is the preferable polymer binder. The polyurethane is a solvent-based polyurethane with a preferred concentration of 35% solids to 65% solvent, the solvent being comprised of 65% dimethylformamide, 25% toluene and 10% methyl ethyl ketone. One such polyurethane is BC-400™ obtained

phase change mechanism. These heat storage and transfer properties do not suffer degradation in thermal performance when the coated fabric is compressed, as experienced by materials which solely depend upon
5 insulative-trapped air for their barrier properties.

In another important aspect of the invention, clothing with thermal barrier properties can be fabricated from coated fabric substrates. The latent energy stored in the phase change material can be
10 "recharged" by metabolic heat production during high activity levels, as well as by an external heat source applied prior to use. For example, a protective glove-liner can be made from a coated fabric. With the appropriate phase change material, the glove-liner can be
15 adapted for cold weather use. The glove-liner can be heated prior to use to saturate the latent energy storage of the phase change material. It will remain warm for an extended period of time, with substantial cooling not occurring until the liquid phase change material has
20 solidified, the length of time depending upon the metabolic activity of the user and the external temperature. Conversely, by selecting the appropriate phase change material, the glove-liner can be used to handle hot objects. In this instance, the phase change
25 material is applied in the "cooled" state. When exposed to a hot environment, the user will remain comfortable until the phase change material has changed state.

Furthermore, the usefulness of the coating may be extended by using microcapsules containing two or more
30 different phase change materials. Thus, by proper selection, a glove may be designed to protect the hand of the wearer when grasping hot objects and to similarly warm the hand of the user when out in a cold environment. It will be noted that this effect is reversible. The
35 concept can be applied to items of clothing such as shoes, environmental suits, and numerous other

applications which require protecting individuals or machinery from the hot or cold.

5 The foregoing embodiments and examples are to be considered illustrative, rather than restrictive of the invention, and those modifications which come within the meaning and equivalence of the claims are to be included therein.

WHAT IS CLAIMED:

1. A coating adapted to be applied to a substrate such as a fabric or a fiber for enhancing the thermal storage properties thereof and consisting essentially of:

5 a liquid polymer binder, and
a plurality of leak resistant microcapsules dispersed throughout said liquid polymer binder, said microcapsules containing a temperature stabilizing means; and when said liquid polymer containing microcapsules

10 bonds with the substrate, upon application thereto the substrate exhibits enhanced thermal stability when the coating thus applied is cured and is subjected to heat or cold.

2. A coating according to claim 1 wherein said

15 temperature stabilizing means comprises a phase change material selected from the group of paraffinic hydrocarbons.

3. A coating according to claim 1 wherein said temperature stabilizing means comprises plastic crystals.

20 4. A coating according to claim 2 wherein said microcapsules range in diameter from about 0.5 microns to about 1,000 microns.

5. An article such as a fabric or fiber having enhanced thermal storage properties and repeatability of

25 thermal response and consisting essentially of:

a base material, and
a coating covering at least a portion of said base material and comprising:

a binder, and

30 a plurality of microcapsules dispersed throughout and submerged within said binder so as to be surrounded thereby, said microcapsules containing a temperature stabilizing means, whereby the article exhibits enhanced thermal stability when subjected to

35 heat or cold.

6. An article having enhanced thermal storage properties according to Claim 5 wherein said microcapsules are leak resistant, whereby the article may be subjected to repeated mechanical stresses with minimum changes in the thermal characteristics thereof.

7. An article with reversible enhanced thermal storage properties according to Claim 5 wherein said temperature stabilizing means comprises a phase change material.

8. An article with reversible enhanced storage properties according to Claim 5 wherein said temperature stabilizing means comprises a material selected from the group of paraffinic hydrocarbons.

9. An article with reversible enhanced thermal storage properties according to Claim 5 wherein said temperature stabilizing means comprises a plastic crystal.

10. An article with reversible enhanced thermal storage properties according to Claim 5 wherein said microcapsules range in diameter from about 0.5 to 1,000 microns.

11. An article with reversible enhanced thermal storage properties according to Claim 5 wherein the coating includes at least two types of separately encapsulated temperature stabilizing means.

12. An article according to Claim 5 wherein said binder is a polymer selected from the group consisting of polyurethane, nitrile rubber, chloroprene rubber, polyvinyl chloride, silicone, ethylene/vinyl acetate copolymer, and acrylic.

13. A method of improving the thermal capacity of a substrate such as a fabric or fiber comprising the steps of:

(a) applying directly to the surface of the substrate a liquid polymer having a plurality of microcapsules containing thermal energy storage compound

dispersed throughout the liquid polymer, the polymer being present in sufficient quantity to cover and surround said microcapsules, and

5 (b) curing the polymer so that the polymer and the microcapsules adhere to the surface of the substrate.

14. The method according to Claim 13 wherein the thermal energy storage compound is a phase change material.

10 15. The method according to Claim 13 wherein the thermal energy storage compound is a plastic crystal.

16. The method according to Claim 14 wherein the microcapsules have a diameter between about 0.5 microns and about 1,000 microns.

15 17. A fabric consisting essentially of, in combination:

(a) a base fabric substrate, and

(b) a flexible polymer directly coating covering at least a portion of said substrate, a
20 plurality of microcapsules dispersed throughout said coating so as to be covered and surrounded thereby, said microcapsules containing a temperature stabilizing means, whereby the coated substrate exhibits enhanced thermal stability when subjected to heat or cold.

25 18. A fabric according to Claim 17, wherein said substrate is a tightly woven fabric and said coating covers a portion of the outer surface of thereof forming a continuous layer.

30 19. A fabric according to Claim 17, wherein said substrate is a loosely woven fabric composed of a plurality of individual fibers and wherein said coating covers the entire circumference of the individual fibers forming a discontinuous layer.

35 20. A thermal control material with reversible thermal storage properties according to Claim 17 wherein

said temperature stabilizing means comprises a phase change material.

21. The coating according to claim 2 wherein the paraffinic hydrocarbon is selected from the group
5 consisting of n-Octacosane, n-Heptacosane, n-Hexacosane, n-Pentacosane, n-Tetracosane, n-Tricosane, n-Docosane, n-Heneicosane, n-Eicosane, n-Nonadecane, n-Octadecane, n-Heptadecane, n-Hexadecane, n-Pentadecane, n-Tetradecane, and n-Tridecane.

10 22. The coating according to claim 2 wherein the paraffinic hydrocarbon has a melting point between about -5.5 degrees Centigrade and about 61.4 degrees Centigrade.

23. The article according to claim 8 wherein the
15 paraffinic hydrocarbon is selected from the group consisting of n-Octacosane, n-Heptacosane, n-Hexacosane, n-Pentacosane, n-Tetracosane, n-Tricosane, n-Docosane, n-Heneicosane, n-Eicosane, n-Nonadecane, n-Octadecane, n-Heptadecane, n-Hexadecane, n-Pentadecane,
20 n-Tetradecane, and n-Tridecane.

24. The article according to claim 8 wherein the paraffinic hydrocarbon has a melting point between about -5.5 degrees Centigrade and about 61.4 degrees Centigrade.

25 25. The method according to claim 14 wherein the phase change material is selected from the group of paraffinic hydrocarbons consisting of n-Octacosane, n-Heptacosane, n-Hexacosane, n-Pentacosane, n-Tetracosane, n-Tricosane, n-Docosane, n-Heneicosane,
30 n-Eicosane, n-Nonadecane, n-Octadecane, n-Heptadecane, n-Hexadecane, n-Pentadecane, n-Tetradecane, and n-Tridecane.

26. The method according to claim 14 wherein the phase change material comprises a paraffinic hydrocarbon
35 having a melting point between about -5.5 degrees Centigrade and about 61.4 degrees Centigrade.

27. The fabric according to claim 20 wherein the phase change material is selected from the group consisting of n-Octacosane, n-Heptacosane, n-Hexacosane, n-Pentacosane, n-Tetracosane, n-Tricosane, n-Docosane,
5 n-Heineicosane, n-Eicosane, n-Nonadecane, n-Octadecane, n-Heptadecane, n-Hexadecane, n-Pentadecane, n-Tetradecane, and n-Tridecane.

28. The fabric according to claim 20 wherein the phase change material comprises a paraffinic hydrocarbon
10 having a melting point between about -5.5 degrees Centigrade and about 61.4 degrees Centigrade.

29. The coating according to Claim 1 wherein the liquid polymer binder is comprised of polyurethane, the microcapsules have an average diameter of from 10 to 60
15 microns and the temperature stabilizing means is octadecane.

30. The article according to Claim 5 wherein the binder is a polyurethane, the microcapsules have an average diameter of from 10 to 60 microns and the
20 temperature stabilizing means is octadecane.

31. The method according to Claim 13 wherein the liquid polymer is polyurethane and wherein the applying step comprises spraying the polyurethane with microcapsules dispersed therein on the substrate.

25 32. The fabric according to Claim 17 wherein the flexible polymer is polyurethane and the temperature stabilizing means comprises octadecane.

Fig. 2




Fig. 3




Fig. 1




Fig. 4





Fig. 5



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/05119

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : B05D 3/00; B32B 5/24; D02G 3/00; D03D 25/00

US CL : 428/262, 283, 402.21, 378; 427/389.9, 394

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 428/262, 283, 402.21, 378; 427/389.9, 394

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 4,756,958 (BRYANT) 12 JULY 1988. See entire document.	1-32
Y	US, A, 4,774,133 (DOREE) 27 SEPTEMBER 1988. See column 2, lines 24-57.	1-32

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be part of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Z" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 10 AUGUST 1993	Date of mailing of the international search report 16 SEP 1993
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. NOT APPLICABLE	Authorized officer CHRISTOPHER BROWN Telephone No. (703) 308-2351